

# BLUE FLUTE

Lightweight recycled fluting made of 100% selected recycled fibres.  
Lightens the final product with the best runability.

Grade Description	Nominal grammage g/m <sup>2</sup>	CMT 30 N	SCT cd kN/m
Test method	ISO 536	ISO 7263	ISO 9895
Tolerance	+/- 3%	Guaranteed/Typical	Guaranteed/Typical
Blue Flute 80 g/m <sup>2</sup>	80	- / 109	1.19 / 1.32
Blue Flute 85 g/m <sup>2</sup>	85	- / 119	1.29 / 1.43
Blue Flute 90 g/m <sup>2</sup>	90	- / 129	1.39 / 1.54
Blue Flute 95 g/m <sup>2</sup>	95	- / 139	1.44 / 1.60
Blue Flute 100 g/m <sup>2</sup>	100	149 / 165	1.49 / 1.65
Blue Flute 105 g/m <sup>2</sup>	105	158 / 176	1.58 / 1.76
Blue Flute 110 g/m <sup>2</sup>	110	168 / 187	1.68 / 1.87
Blue Flute 120 g/m <sup>2</sup>	120	178 / 198	1.78 / 1.98
Blue Flute 125 g/m <sup>2</sup>	125	188 / 209	1.88 / 2.09

Moisture content : 7,5 +/- 0,5% (ISO 287)  
Test conditions : 23°- 50% RH (ISO 187)

Valid: from May 2024



Blue Paper SAS  
4, rue Charles Friedel  
CS 30009  
F - 67017 Strasbourg Cedex

✉ sales@bluepaper.eu  
🌐 www.bluepaper.eu  
☎ +33 3 88 41 75 32  
🖨 +33 3 88 41 75 98